

ALPHA WIRE & ROD SALES

CONTACT:
800-368-2111
PAUL OR MARK
info@strohauermarketing.com

EXCLUSIVE SALES AGENTS
STROHAUER MKTG. GROUP
3669 VALLEY HILL ROAD
KENNESAW, GA 30152

PHONE: 800-368-2111
FAX: 770-424-9900
STOCKING LOCATION:
DANIELSON, CT 06239



www.StrohauerMarketing.com
www.SMG.bz

July 21, 2010 INVENTORY

DESCRIPTION					CHEMISTRY											
TYPE	SIZE	HEAT	STATUS	QUANTITY	TENSILE	C	Mn	P	S	Si	Cr	Ni	Mo	Cu	N	Co
302^	0.217	3HP4	INSTK	12118	91000	0.072	1.04	0.030	0.001	0.560	18.04	8.73	0.29	0.41	0.058	0.1646
302^	0.218	672-1762	INSTK	19862	91436	0.090	0.98	0.028	0.012	0.100	18.56	8.20	0.12	0.43	0.088	
304	0.217	234863	INSTK	302	81221	0.039	1.73	0.024	0.006	0.360	18.11	8.16	0.08	0.27	370PPM	
304^	0.218		ONORDER	38082												
304^	0.218		ONORDER	37868												
305^	0.218	93H2	INSTK	714	78796	0.020	1.21	0.028	0.001	0.321	18.63	11.44	0.26	0.33	0.025	
305	0.354	A77972	INSTK	793	76000	0.041	0.67	0.025	0.004	0.421	18.06	12.06	0.22	0.34		
305^	0.472	250014	INSTK	2002		0.024	1.81	0.026	0.002	0.320	18.51	10.51			540PPM	
305^	0.591	E52820	INSTK	10502	73004	0.018	0.85	0.028	0.002	0.390	18.20	11.34	0.33	0.40	340PPM	0.148
410*	0.217	10116010433	INSTK	16213	74675	0.090	0.36	0.025	0.006	0.380	12.20	0.14	0.03	0.10	0.050	
410*	0.236	10116010432	INSTK	3042	71775	0.100	0.45	0.023	0.009	0.380	12.31	0.14	0.03	0.09	0.050	
410*	0.256	10116027190	INSTK	3058	81200	0.110	0.41	0.021	0.004	0.470	12.85	0.13	0.03	0.18	0.050	
410^	0.256		ONORDER	7000												
410^	0.276		ONORDER	10000												
410*	0.276		ONORDER	19000												
410*	0.295	10116010433	INSTK	17838	74675	0.090	0.36	0.025	0.006	0.380	12.20	0.14	0.03	0.10	0.050	
410*	0.315	10116010432	INSTK	18089	71775	0.100	0.45	0.023	0.009	0.380	12.31	0.14	0.03	0.09	0.050	
410*	0.315	10116010432	INSTK	2506	71775	0.100	0.45	0.023	0.009	0.380	12.31	0.14	0.03	0.09	0.050	
410*	0.335	10116010432	INSTK	11312	71775	0.100	0.45	0.023	0.009	0.380	12.31	0.14	0.03	0.09	0.050	
410*	0.335		ONORDER	9500												
410*	0.354	10116010433	INSTK	4300	74675	0.090	0.36	0.025	0.006	0.380	12.20	0.14	0.03	0.10	0.050	
410*	0.354		ONORDER	19000												
410*	0.374		ONORDER	9500												
410*	0.393		ONORDER	9500												
410^	0.393	08116010599	INSTK	2429	78300	0.100	0.38	0.022	0.003	0.330	12.33	0.20	0.07	0.13	0.025	
410^	0.413	63-1001	INSTK	4281		0.110	0.31	0.016	0.006	0.290	12.46	0.10	0.00	0.14	0.039	
410^	0.413	63-2040	INSTK	9180	75400	0.090	0.31	0.019	0.002	0.390	12.40	0.10	0.01	0.12	0.026	
410^	0.413	08116020521	INSTK	8898	69600	0.110	0.22	0.016	0.010	0.370	12.14	0.08	0.00	0.10	0.028	
410*	0.472	08116021556	INSTK	1919	78320	0.100	0.46	0.027	0.003	0.340	12.60	0.11		0.15		
410*	0.472	10116010140	INSTK	5198	79750	0.120	0.54	0.023	0.009	0.370	12.41	0.14	0.01	0.17	0.034	
410*	0.472	10116010140	INSTK	1417	79750	0.120	0.54	0.023	0.009	0.370	12.41	0.14	0.01	0.17	0.034	
410*	0.492	09116012017	INSTK	9557	79771	0.120	0.32	0.025	0.002	0.330	12.61	0.18	0.05	0.17		
410*	0.492	09116022190	INSTK	9442		0.110	0.37	0.024	0.011	0.390	12.10	0.32	0.04	0.21	0.025	
410*	0.492		ONORDER	19000												
410*	0.512	10116010140	INSTK	5948	79750	0.120	0.54	0.023	0.009	0.370	12.41	0.14	0.01	0.17	0.034	
410*	0.512		ONORDER	9500												
410^	0.551	09116010970	INSTK	19090	79025	0.100	0.31	0.022	0.002	0.380	12.16	0.31	0.01	0.18	0.030	
410*	0.591	10116010432	INSTK	21195	71775	0.100	0.45	0.023	0.009	0.380	12.31	0.14	0.03	0.09	0.050	
410^	0.591	09116011246	INSTK	6300	82650	0.100	0.40	0.022	0.003	0.440	12.35	0.25	0.06	0.17		
410*	0.591	09116021989	INSTK	15245	79025	0.090	0.40	0.024	0.004	0.470	12.69	0.18	0.05	0.19	0.025	
410*	0.591		ONORDER	19000												
416*	0.236		ONORDER	9500												
416^	0.315	7107030676	INSTK	17558	87000	0.120	1.03	0.026	0.340	0.580	12.96	0.07	0.01	0.09	0.020	
416^	0.335	07107030565	INSTK	13704	81925	0.120	0.51	0.023	0.260	0.500	12.78	0.10	0.10	0.10	0.018	
416*	0.354		ONORDER	9500												

ALPHA WIRE & ROD SALES

CONTACT:
800-368-2111
PAUL OR MARK
info@strohauermarketing.com

EXCLUSIVE SALES AGENTS
STROHAUER MKTG. GROUP
3669 VALLEY HILL ROAD
KENNESAW, GA 30152

PHONE: 800-368-2111
FAX: 770-424-9900
STOCKING LOCATION:
DANIELSON, CT 06239



www.StrohauerMarketing.com
www.SMG.bz

July 21, 2010 INVENTORY

DESCRIPTION					CHEMISTRY											
TYPE	SIZE	HEAT	STATUS	QUANTITY	TENSILE	C	Mn	P	S	Si	Cr	Ni	Mo	Cu	N	Co
416^	0.413	63-1676	INSTK	5485	83375	0.140	0.92	0.022	0.340	0.420	12.70	0.16	0.02	0.12	0.020	
420^	0.218		ONORDER	10000												
420^	0.256	08116010485	INSTK	2500	93549	0.270	0.41	0.028	0.005	0.300	13.00	0.15	0.02	0.13	0.011	
420^	0.335	08116010486	INSTK	3069	92824	0.250	0.46	0.025	0.003	0.260	13.25	0.14	0.01	0.14	0.010	
420^	0.374	08116010485	INSTK	8909	86275	0.270	0.41	0.028	0.005	0.300	13.00	0.15	0.02	0.13	0.011	
420^	0.374	63-1020	INSTK	5056	94975	0.260	0.48	0.032	0.005	0.290	13.19	0.17	0.01	0.13	0.060	
430L^	0.218	519354	INSTK	655	61103	0.016	0.53	0.013	0.002	0.270	16.63	0.14	0.02	0.02	0.018	0.025
430L^	0.218		ONORDER	13500												
430^	0.235	6KC7		6786												
430L*	0.236	09116012219	INSTK	2174	63817	0.030	0.49	0.021	0.006	0.210	16.50	0.13	0.02	0.14	.03ppm	0.026
430L*	0.236	09116012139	INSTK	5388	66717	0.030	0.35	0.022	0.013	0.310	16.90	0.17	0.05	0.16	.025ppm	0.028
430L*	0.256	09116012219	INSTK	8386	68893	0.030	0.49	0.021	0.006	0.210	16.50	0.13	0.02	0.14	.03ppm	0.026
430L*	0.276	09116022390	INSTK	3937	68150	0.024	0.32	0.028	0.006	0.210	16.80	0.29	0.06	0.16	0.044	0.025
430L^	0.276		ONORDER	18000												
430L*	0.335	09116012219	INSTK	2705	65992	0.030	0.49	0.021	0.006	0.210	16.50	0.13	0.02	0.14	.03ppm	0.026
430L*	0.335	09116012139	INSTK	6301	68618	0.030	0.35	0.022	0.013	0.310	16.90	0.17	0.05	0.16	.025ppm	0.028
430L*	0.335	09116022390	INSTK	9374	68150	0.024	0.32	0.028	0.006	0.210	16.80	0.29	0.06	0.16	0.044	0.025
430L*	0.354	09116022093	INSTK	8682	66700	0.021	0.17	0.025	0.005	0.430	17.78	0.31	0.04	0.17	0.030	0.03
430L*	0.374		ONORDER	9500												
430L*	0.393		ONORDER	19000												
430L*	0.433		ONORDER	19000												
430*	0.433	10106027833	INSTK	10364	60900	0.015	0.49	0.022	0.004	0.420	16.70	0.17	0.02	0.11	0.010	
430L*	0.472		ONORDER	9500												
430L^	0.515		ONORDER	9000												
430*	0.515	6FE8	INSTK	2819	66020	0.029	0.46	0.024	0.001	0.210	16.39	0.29	0.03	0.14	0.025	0.02
430*	0.531	452290	INSTK	657		0.009	0.40	0.020	0.001	0.410	16.99	0.25	0.01	0.03	0.026	0.03
430L*	0.535	6FE8	INSTK	9280	66590	0.029	0.46	0.024	0.001	0.210	16.39	0.29	0.03	0.14	0.025	0.02
430^	0.709	941168	INSTK	310	63860	0.020	0.36	0.020	0.012	0.230	16.80	0.10	0.02	0.08	0.023	
431*	0.250	63-2291	INSTK	1040	148645	0.160	0.43	0.028	0.003	0.350	15.66	2.16	0.05	0.12	0.051	
431*	0.250	08116021865	INSTK	2814	138423	0.200	0.38	0.030	0.012	0.260	15.78	2.10	0.08	0.14	0.030	
431	0.276	08116021865	INSTK	2056	134160	0.200	0.38	0.030	0.012	0.260	15.78	2.10	0.08	0.14	0.030	
204Cu	0.187	14211	INSTK	40635	123470	0.070	7.42	0.039	0.009	0.510	16.26	1.83		2.13	0.166	
204CU^	0.218	152869	INSTK	1202	89985	0.095	8.41	0.051	0.003	0.350	15.97	2.17	0.06	2.35	1390PPM	
204CU^	0.256	247808	INSTK	2840	90130	0.048	8.02	0.030	0.002	0.410	15.85	2.21	0.05	2.21	1200PPM	
204CU^	0.276	248201	INSTK	1499	87808	0.073	8.15	0.040	0.003	0.310	15.75	2.22	0.05	2.29	1270PPM	
204CU^	0.281	248622	INSTK	1373	89695	0.065	8.53	0.051	0.003	0.310	15.74	2.17	0.05	2.18	1240PPM	
204CU^	0.315	247800	INSTK	11018	90130	0.052	8.09	0.032	0.005	0.410	15.88	2.13	0.06	2.27	1330PPM	
204CU^	0.315	248200	INSTK	2786	87953	0.072	8.20	0.039	0.004	0.330	15.64	2.24	0.05	2.17	1260PPM	
204CU^	0.315	248202	INSTK	8498	85486	0.053	8.31	0.035	0.003	0.270	15.75	2.17	0.05	2.22	1150PPM	
302HQ*	0.217	E82051	INSTK	1539	69618	0.010	0.61	0.026	0.001	0.419	17.69	9.62	0.14	3.19	0.015	0.08
302HQ*	0.217		ONORDER	10500												
302HQ^	0.224		ONORDER	20000												
302HQ*	0.256		ONORDER	10500												
302HQ*	0.276		ONORDER	3500												
302HQ*	0.315		ONORDER	10500												

ALPHA WIRE & ROD SALES

CONTACT:
800-368-2111
PAUL OR MARK
info@strohauermarketing.com

EXCLUSIVE SALES AGENTS
STROHAUER MKTG. GROUP
3669 VALLEY HILL ROAD
KENNESAW, GA 30152

PHONE: 800-368-2111
FAX: 770-424-9900
STOCKING LOCATION:
DANIELSON, CT 06239



www.StrohauerMarketing.com
www.SMG.bz

July 21, 2010 INVENTORY

DESCRIPTION					CHEMISTRY											
TYPE	SIZE	HEAT	STATUS	QUANTITY	TENSILE	C	Mn	P	S	Si	Cr	Ni	Mo	Cu	N	Co
302HQ*	0.335		ONORDER	10500												
302HQ*	0.354		ONORDER	10500												
302HQ2^	0.354	E71183	INSTK	1055	68505	0.013	0.73	0.027	0.001	0.280	17.61	9.73	0.21	3.40	150PPM	
302HQ*	0.374	253306	INSTK	3510	67298	0.015	1.73	0.032	0.005	0.280	17.40	8.08	0.07	3.31	220ppm	
302HQ*	0.354		ONORDER	10500												
302HQ*	0.394		ONORDER	10500												
302HQ1^	0.413		ONORDER	7000												
302HQ1^	0.453		ONORDER	7000												
302HQ1^	0.472	248643	INSTK	10681	67779	0.014	1.73	0.034	0.003	0.240	17.40	8.10	0.14	3.15	200PPM	
302HQ1^	0.472	250883	INSTK	3405	67924	0.019	1.73	0.033	0.005	0.190	17.64	8.13	0.28	3.36	140PPM	
302HQ2^	0.472	E71956	INSTK	1984	67053	0.009	0.71	0.027	0.001	0.270	17.61	9.61	0.20	3.44	140PPM	
302HQ*	0.512		ONORDER	10500												
302HQ^	0.535	80Y6	INSTK	1849	81000	0.025	0.49	0.018	0.002	0.401	17.66	10.00	0.04	3.35	0.021	0.0472
302HQ1^	0.709	155348	INSTK	7227	67489	0.015	1.62	0.031	0.004	0.190	17.23	8.18	0.10	3.46	130PPM	
303F*	0.078	S60532	INSTK	338		0.051	2.93	0.028	0.321	0.410	18.17	9.18				
303F*	0.078	S61426	INSTK	358		0.041	2.88	0.028	0.322	0.380	18.30	9.28				
303F*	0.100	S60532	INSTK	161	110000	0.051	2.93	0.028	0.321	0.410	18.17	9.18				
303F*	0.100	S61426	INSTK	157	110000	0.041	2.88	0.028	0.322	0.380	18.30	9.28				
303F	0.100	S61426	INSTK	3852	110000	0.041	2.88	0.028	0.322	0.380	18.30	9.28				
304H*	0.217	E81234	INSTK	422	82962	0.063	1.30	0.030	0.003	0.383	18.43	8.34	0.01	0.37	0.041	0.145
304H^	0.218		ONORDER	70133												
304H^	0.218		ONORDER	37500												
304L1^	0.256	159354	INSTK	14148	82728	0.025	1.84	0.031	0.006	0.310	18.29	8.07	0.04	0.56	PPM 770	
304L^	0.295		ONORDER	17000												
304L*	0.315		ONORDER	10500												
304L*	0.374		ONORDER	10500												
304L*	0.375	255626	INSTK	3576	81221	0.020	1.71	0.035	0.006	0.330	18.11	8.11	0.07	0.51	800ppm	
304L*	0.375	256079	INSTK	3571	80641	0.024	1.75	0.029	0.004	0.340	18.16	8.10	0.07	0.54	720ppm	
304L*	0.413	256431	INSTK	10752	81076	0.026	1.79	0.030	0.009	0.370	18.35	8.10	0.14	0.65	750ppm	
304L^	0.413	248580	INSTK	946	82236	0.026	1.63	0.031	0.009	0.290	18.23	8.09	0.14	0.49	720ppm	
304L*	0.413		ONORDER	10500												
304L*	0.512		ONORDER	10500												
304M4^	0.276		ONORDER	14000												
304M4	0.276	241990	INSTK	790	84847	0.044	1.77	0.035	0.005	0.360	18.27	8.18	0.06	0.21	340PPM	
304M^	0.276	239890	INSTK	782	80261	0.041	1.84	0.030	0.008	0.330	18.45	9.28	0.08	0.13	PPM420	
304M4^	0.295		ONORDER	14000												
304M^	0.394	240253	INSTK	3574	78229	0.045	1.77	0.028	0.003	0.440	18.25	9.28	0.07	0.19	390PPM	
304M4^	0.394	243613	INSTK	6999	83599	0.039	1.76	0.032	0.007	0.410	18.20	8.08	0.14	0.28	350PPM	
304M4^	0.394	541145	INSTK	7120	85341	0.038	1.74	0.028	0.010	0.370	18.35	8.04	0.08	0.16	360PPM	
310S*	0.218	739393	INSTK	1406												
316L*	0.218		ONORDER	10500												
316L*	0.236	E91409	INSTK	3472	79916	0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316L*	0.256		ONORDER	10500												
316L^	0.276		ONORDER	13500												
316LCu^	0.276	719134	INSTK	6553	75000	0.020	0.62	0.028	0.001	0.560	16.63	10.04	2.05	3.39	0.015	

**ALPHA WIRE &
ROD SALES**

CONTACT:
800-368-2111
PAUL OR MARK
info@strohauermarketing.com

EXCLUSIVE SALES AGENTS
STROHAUER MKTG. GROUP
3669 VALLEY HILL ROAD
KENNESAW, GA 30152

PHONE: 800-368-2111
FAX: 770-424-9900
STOCKING LOCATION:
DANIELSON, CT 06239



www.StrohauerMarketing.com
www.SMG.bz

July 21, 2010 INVENTORY

DESCRIPTION					CHEMISTRY											
TYPE	SIZE	HEAT	STATUS	QUANTITY	TENSILE	C	Mn	P	S	Si	Cr	Ni	Mo	Cu	N	Co
316L*	0.276	E91409	INSTK	5969	78901	0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316L*	0.295	E91409	INSTK	3987		0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316L*	0.315	E91409	INSTK	10454	78175	0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316LCu^	0.315	719134	INSTK	18940	80497	0.020	0.62	0.028	0.001	0.560	16.63	10.04	2.05	3.39	0.015	
316L*	0.315	E90738	INSTK	10474	80496	0.012	1.51	0.029	0.001	0.530	17.24	10.14	2.05	0.35	330ppm	
316L*	0.345	RYL-1292	INSTK	1049	112225	0.017	1.24	0.035	0.007	0.430	16.20	10.00	2.02	0.45	0.062	
316L*	0.354		ONORDER	10500												
316L*	0.375	E91409	INSTK	10465		0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316L^	0.373	15677	INSTK	840	84500	0.017	1.24	0.035	0.007	0.430	16.20	10.02	2.02	0.50		
316L*	0.374	E90738	INSTK	10503	80061	0.012	1.51	0.029	0.001	0.530	17.24	10.14	2.05	0.35	330ppm	
316L*	0.393	E91409	INSTK	6976	77450	0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316L*	0.393	E91409	INSTK	2190	77450	0.015	1.53	0.030	0.001	0.530	17.17	10.10	2.06	0.30	350ppm	
316L*	0.394	E90738	INSTK	3521	79916	0.012	1.51	0.029	0.001	0.530	17.24	10.14	2.05	0.35	330ppm	
316L*	0.394	E90738	INSTK	1800	79916	0.012	1.51	0.029	0.001	0.530	17.24	10.14	2.05	0.35	330ppm	
316L*	0.445	RYL-1293	INSTK	1912	102318	0.022	1.21	0.030	0.010	0.390	16.20	10.03	2.02	0.42	0.059	
316L*	0.453	E90738	INSTK	3508	79046	0.012	1.51	0.029	0.001	0.530	17.24	10.14	2.05	0.35	330ppm	
316L*	0.453	E100046	INSTK	6984	78030	0.012	1.55	0.031	0.002	0.530	17.16	10.08	2.06	0.41	350ppm	
316L*	0.453		ONORDER	10500												
316L*	0.472	E100046	INSTK	10494	78465	0.012	1.55	0.031	0.002	0.530	17.16	10.08	2.06	0.41	350ppm	
316L*	0.512	E100046	INSTK	3459	79191	0.012	1.55	0.031	0.002	0.530	17.16	10.08	2.06	0.41	350ppm	
316L*	0.531	E100255	INSTK	10386	78901	0.013	1.42	0.029	0.002	0.520	17.30	10.04	2.01	0.43	340ppm	
316L*	0.531	E90592	INSTK	1155	74550	0.019	1.69	0.029	0.002	0.383	17.26	11.09	2.04	0.36	0.035	0.352
316L^	0.531		ONORDER	9000												
316L*	0.531	E90740	INSTK	6960	78031	0.021	1.55	0.029	0.003	0.550	17.26	10.11	2.04	0.44	320ppm	
316L*	0.531	E90740	INSTK	1875	78031	0.021	1.55	0.029	0.003	0.550	17.26	10.11	2.04	0.44	320ppm	
316L*	0.591		ONORDER	10500												
316L1^	0.709	249086	INSTK	3604	80696	0.015	1.51	0.030	0.003	0.550	17.35	10.16	2.01	0.27	110PPM	
316L^	0.709	418301	INSTK	2326	82293	0.025	1.24	0.028	0.030	0.500	17.58	11.02	2.00	0.55	0.064	0.073
317L*	0.354	518821	INSTK	6617	82383	0.010	1.38	0.019	0.010	0.410	18.78	13.59	3.56	0.12	0.041	0.042
317L*	0.472	518821	INSTK	4482	82383	0.010	1.38	0.019	0.010	0.410	18.78	13.59	3.56	0.12	0.041	0.042
317L*	0.472	518821	INSTK	4482	82383	0.010	1.38	0.019	0.010	0.410	18.78	13.59	3.56	0.12	0.041	0.042
321*	0.217	E91027	INSTK	14652	80786	0.045	1.50	0.030	0.001	0.462	17.13	9.06	0.26	0.38	0.015	0.112
430F^	0.217	7107030286	INSTK	17200	74675	0.027	0.67	0.018	0.390	0.590	17.71	0.40	0.02	0.18	0.030	
430F^	0.276	7107030286	INSTK	5110	79750	0.027	0.67	0.018	0.390	0.590	17.71	0.40	0.02	0.18		
M400^	0.217	CL206	INSTK	3018	77793	0.050	0.97	0.001	0.002	0.140		64.55		32.67		